



® Management Procedure 2584

Revision: A

Date Issued: July 11, 2019

Date Revised:

## Calibration Procedure

DeFelsko Corporation

PosiTector 6000 FJS

Coating Thickness Probe

### Table of Contents

1	Introduction and UUC Performance Requirements.....	2
	Table 1-1 Measurement Ranges .....	2
2	Measurement Standards and Support Equipment Performance Requirements.....	2
	Table 2-1 UUC Accuracy Requirements and Description.....	2
	Table 2-2 Minimum use specification .....	2
	Table 2-3 Actual Equipment Specification.....	2
	Table 2-4 Calibration Environmental and Warm-Up Requirements .....	3
3	Preliminary Operations.....	3
4	Calibration Process .....	4
5	Performance Requirements.....	5
	Table 5-1 Performance Requirements and Calibration Data for PosiTector 6000 FJS .....	5
	Management Procedure Change Notice .....	6

# 1 Introduction and UUC Performance Requirements

1.1 This procedure describes the calibration of DeFelsko Corporation PosiTector 6000 FJS probe with the following specifications:

Table 1-1 Measurement Ranges

Probe	Measurement Range
6000 FJS	0 – 25 mm (0 – 1 in)

1.2 The unit being calibrated will be referred to as the UUC (Unit-Under-Calibration).

# 2 Measurement Standards and Support Equipment Performance Requirements

2.1 The UUC accuracy requirements are based upon the published UUC performance specifications.

2.2 The test uncertainty ratio applied in this Calibration Procedure is 4:1 unless otherwise stated.

2.3 The Minimum-Use-Specifications are the minimum test equipment specifications required to meet all the UUC accuracy requirements and the test uncertainty ratio applied.

Table 2-1 UUC Accuracy Requirements and Description

UUC	Performance Specifications		Test Method
6000 FJS	0 – 25 mm (0 – 1 in)	$\pm (0.2 \text{ mm} + 3\% \text{ of reading})$ $\pm (0.01 \text{ in} + 3\% \text{ of reading})$	Compared to Reference Standards

Table 2-2 Minimum use specification

Range	Accuracy
0 – 25 mm (0 – 1 in)	$\pm 0.05 \text{ mm}$ ( $\pm 2.5 \text{ mils}$ )

Table 2-3 Actual Equipment Specification

Equipment Generic Name	Range	Accuracy	Manufacturer / Model #'s Applicable
Certified Polystyrene Blocks	2.5 – 19 mm (100 - 750 mils)	$\pm (0.0025 \text{ mm} + 0.05\% \text{ of thickness})$ $\pm (0.1 \text{ mil} + 0.05\% \text{ of thickness})$	DeFelsko Corporation, STD-P2

**Caution:** The instructions in this Calibration Procedure relate specifically to the equipment and conditions listed in Section 2. If other equipment is substituted, the information and instructions must be interpreted accordingly.

Table 2-4 Calibration Environmental and Warm-Up Requirements

Measurement Standards & Support Equipment Environmental Requirements:	Temperature: $23 \pm 5^{\circ}$ C. Relative Humidity: Less than 95%
Measurement Standards & Support Equipment Warm-up and Stabilization Requirements:	Not Required

### 3 Preliminary Operations

**Note:** Review the entire document before starting the calibration process.

3.1 Visually inspect the measurement face of the probe for signs of damage or excessive wear, this could impact probe accuracy.

#### 3.2 Gage Reset

3.2.1 When the unit is powered down, simultaneously hold the “+” and middle buttons for several seconds then release them. Once the buttons are released the reset symbol will appear.

**Caution:** Be sure to hold the probe in the air and well away from any metal surface during the RESET process.

#### 3.3 Probe Zero Calibration Adjustment

3.3.1 While holding the probe in the air, select the Cal Settings “Zero” function and then indicate the number of readings (1) to be used.

3.3.2 Measure the middle of a flat uncoated (zero) 1018 steel plate at least 7” x 7” x 1/4”.

3.3.3 Re-measure the zero plate. If the reading is within +/-0.2 mm (10 mil) continue, otherwise repeat steps 3.3.1 and 3.3.2.

#### 3.4 Material Adjustment

3.4.1 From the Cal Settings menu select 2 pt adjust.

3.4.2 Place the 2.5 mm (100 mil) polystyrene block in the center of the same uncoated plate used to zero the probe and take a reading. Adjust the displayed value to the value of the block. Note: The gage adjusts in 0.02 mm (1 mil) increments.

3.4.3 Place the 19 mm (750 mil) block in the center of the steel plate and stack the 6.5 mm (250 mil) block on top of the 19 mm block, being careful to not have the labels between

the blocks, for a total thickness of 25.5 mm (1000 mil). Take a reading and adjust the displayed value to the total value of the 2 blocks.

## 4 Calibration Process

**Note:** Whenever the test requirement is not met, verify the results of each test and take corrective action before proceeding.

### 4.1 Review the Performance Requirements Table 5-1.

**Note:** The probe calibration may be verified in either normal or high-resolution mode. Accuracy is the same for both modes.

### 4.2 Using the appropriate Certificate of Calibration template for the UUC, record the thickness from the Reference Standards.

### 4.3 Determine the allowed range of readings for the UUC using the calculation methods shown in Table 5-1.

### 4.4 Use the appropriate blocks, stacking if necessary, in the center of the same uncoated plate used to zero the probe to take readings at the following thicknesses: 2.5 mm (100 mil), 6.5 mm (250 mil), 13 mm (500 mil), 19 mm (750 mil) and 25.5 mm (1000 mil). Verify that the readings are within the allowable limits determined in section 4.3. Record the readings on the Certificate of Calibration.

**Note:** Record all digits displayed on the LCD. This may vary depending on the resolution mode. In taking readings the probe shall be centered on the Reference Standards.

## 5 Performance Requirements

**Note:** The technician will collect the data needed to complete columns A and B of the appropriate table below. Do not write in this procedure.

Table 5-1 Performance Requirements and Calibration Data for PosiTector 6000 FJS

Thickness on Reference Standard Label (mm)	Min. Reading Allowed <sup>❶</sup> (mm)	Max. Reading Allowed <sup>❷</sup> (mm)	Actual Probe Measurement (mm)
A			B

❶ Calculation (A times 0.97) – 0.2. Round up to the nearest even 0.02 mm increment

❷ Calculation (A times 1.03) + 0.2. Round down to the nearest even 0.02 mm increment.

\*For imperial/metric readings convert using 1 mil = 0.0254 mm

# Management Procedure Change Notice

Procedure Number: MP 2584

Revision Level: A

Date of Change: July 11, 2019

Title: Calibration Procedure for PosiTector 6000 FJS

Reason for Change: <ul style="list-style-type: none"><li>• New product.</li></ul>
Description of Change: <ul style="list-style-type: none"><li>• New procedure.</li></ul>

I confirm I have read and understand the procedure and the change described above.

Printed Name	Signature	Date

Management Form 0010.02-05/1998